

**LABEKO, s.r.o.**

Krajinská cesta 2929, 921 01 Piešťany, Slovakia  
Accredited testing laboratories  
according to ISO / IEC 17025:2017



Reg. No. 070/S-030

**Test report no.: 25/00817**

Page no. 1 out of 4

**Customer :** Revel Solution s.r.o.  
**(name and address)** Jaurisova 515/4, Michle, 140 00 Praha 4, Czech republic

The date of sample receiving 10.03.25

The date of the test from : 10.03.25  
to : 24.03.25

**Samples taken :** The samples sending by customer

Date of the test report: 25.03.25

**The Test Results**

Ser.No.	1	Sample number	25-000994	Sample type :	Materials and products intended into contact with drinking water
Sample identification :		<b>Ball valve DN25 Series Gold (Art. : GRDV031)</b> <b>The manufacturer : ZHEJIANG FANSHENG FLUID CONTROL CO., LTD,</b> <b>Putian Industrial Area, Chumen Town, Yuhuan City, Zhejiang Province 317605, China</b>			

**Sample Identification :**

The functional surface of the tested product **Ball valve DN25 Series Gold (Art. : GRDV031)** is intended into contact with drinking water. Inner surface material : brass CW617N

The supplied test sample was tested in accordance with the requirements of the Decree of Ministry of Health of the Slovak Republic No. 550/2007 Coll.

**Conditions of migration tests:**

Extracts from submitted samples were prepared according to the Annex to the Decree of Ministry of Health of the Slovak Republic No. 550/2007 Coll.

For migration tests were used two identical samples.

The ratio of the tested surface of the sample to the volume of experimental water :  $45,0 \text{ cm}^2 : 21,0 \text{ cm}^3$  (  $1 \text{ cm}^2 : 0,467 \text{ cm}^3$  )

**Sample pretreatment :**

1. Stagnation :  $(24 \pm 0,5)$  hours at  $(23 \pm 2) ^\circ\text{C}$  in tap water .

2. Rinsing with tap water 60 min. with flow  $(5 \pm 2)$  ml/s and rinsing with experimental water 2 min.

**Migraton test procedure :**

Three consecutive extracts - 72 hour at  $(23 \pm 2) ^\circ\text{C}$  for each extract by using experimental water

Under the same conditions a blank experiment with the experimental water without the tested sample was carried out.

Experimental water : deionised water with the conductivity  $< 2 \text{ mS/m}$  and  $\text{TOC} < (0,2 \pm 0,1) \text{ mg/l}$

The test results are shown in the following tables :

**Table No.1**  
**The sample No. 25-000994 Ball valve DN25 Series Gold (Art. : GRDV031). Measured values for the 1<sup>st</sup> migration test.**

Parameter	Unit	Measured values <sup>1)</sup>			Uncertainty <sup>2)</sup> (k=2)	Methods used	Test <sup>3)</sup> type
		Parallel determinations		Blank			
		K <sub>1</sub>	K <sub>1</sub>	K <sub>0;1</sub>			
Cadmium (Cd)	µg/l	< 1,0	< 1,0	< 1,0		P-01,STN EN ISO 11885	A
Lead (Pb)	µg/l	< 2,0	< 2,0	< 2,0		P-01,STN EN ISO 11885	A
Nickel (Ni)	µg/l	< 2,0	< 2,0	< 2,0		P-01,STN EN ISO 11885	A
Copper (Cu)	mg/l	0,066	0,065	< 0,005	20 %	P-01,STN EN ISO 11885	A
Chromium (Cr)	µg/l	< 5,0	< 5,0	< 5,0		P-01,STN EN ISO 11885	A
Antimony (Sb)	µg/l	< 3,0	< 3,0	< 3,0		P-01,STN EN ISO 11885	A
Tin (Sn)	mg/l	< 0,005	< 0,005	< 0,005		P-01,STN EN ISO 11885	A
Zinc (Zn)	mg/l	0,21	0,22	< 0,005	15 %	P-01,STN EN ISO 11885	A
pH		6,56	6,58	6,52	2 %	P-03, STN ISO 10523	A

K<sub>1</sub> – concentration of migrating substances of the 1<sup>st</sup> parallel migration test for migration time 72 hours and temperature  $(23 \pm 2) ^\circ\text{C}$

K<sub>0;1</sub> – average value of concentration of migrating substances in parallel blank experiment for migration time 72 hours and temperature  $(23 \pm 2) ^\circ\text{C}$

**Test report no.: 25/00817**

Page no. 2 out of 4

**Table No.2**

The sample No. 25-000994 Ball valve DN25 Series Gold (Art. : GRDV031). Measured values for the 2<sup>nd</sup> migration test.

Parameter	Unit	Measured values <sup>1)</sup>			Uncertainty <sup>2)</sup> (k=2)	Methods used	Test <sup>3)</sup> type
		Parallel determinations		Blank			
		K <sub>2</sub>	K <sub>2</sub>	K <sub>0; 2</sub>			
Cadmium (Cd)	µg/l	< 1,0	< 1,0	< 1,0		P-01,STN EN ISO 11885	A
Lead (Pb)	µg/l	< 2,0	< 2,0	< 2,0		P-01,STN EN ISO 11885	A
Nickel (Ni)	µg/l	< 2,0	< 2,0	< 2,0		P-01,STN EN ISO 11885	A
Copper (Cu)	mg/l	0,090	0,100	< 0,005	20 %	P-01,STN EN ISO 11885	A
Chromium (Cr)	µg/l	< 5,0	< 5,0	< 5,0		P-01,STN EN ISO 11885	A
Antimony (Sb)	µg/l	< 3,0	< 3,0	< 3,0		P-01,STN EN ISO 11885	A
Tin (Sn)	mg/l	< 0,005	< 0,005	< 0,005		P-01,STN EN ISO 11885	A
Zinc (Zn)	mg/l	0,15	0,19	< 0,005	20 %	P-01,STN EN ISO 11885	A
pH		6,56	6,54	6,53	2 %	P-03, STN ISO 10523	A

K<sub>2</sub> – concentration of migrating substances of the 2<sup>nd</sup> parallel migration test for migration time 72 hours and temperature (23 ± 2) °C

K<sub>0; 2</sub> – average value of concentration of migrating substances in parallel blank experiment for migration time 72 hours and temperature (23 ± 2) °C

**Table No. 3**

The sample No. 25-000994 Ball valve DN25 Series Gold (Art. : GRDV031). Measured values for the 3<sup>rd</sup> migration test.

Parameter	Unit	Measured values <sup>1)</sup>			Uncertainty <sup>2)</sup> (k=2)	Methods used	Test <sup>3)</sup> type
		Parallel determinations		Blank			
		K <sub>3</sub>	K <sub>3</sub>	K <sub>0; 3</sub>			
Cadmium (Cd)	µg/l	< 1,0	< 1,0	< 1,0		P-01,STN EN ISO 11885	A
Lead (Pb)	µg/l	< 2,0	< 2,0	< 2,0		P-01,STN EN ISO 11885	A
Nickel (Ni)	µg/l	< 2,0	< 2,0	< 2,0		P-01,STN EN ISO 11885	A
Copper (Cu)	mg/l	0,056	0,063	< 0,005	20 %	P-01,STN EN ISO 11885	A
Chromium (Cr)	µg/l	< 5,0	< 5,0	< 5,0		P-01,STN EN ISO 11885	A
Antimony (Sb)	µg/l	< 3,0	< 3,0	< 3,0		P-01,STN EN ISO 11885	A
Tin (Sn)	mg/l	< 0,005	< 0,005	< 0,005		P-01,STN EN ISO 11885	A
Zinc (Zn)	mg/l	0,12	0,13	< 0,005	20 %	P-01,STN EN ISO 11885	A
pH		6,53	6,54	6,51	2 %	P-03, STN ISO 10523	A
Taste ( TFN ) <sup>5)</sup>	deg.	1	1	1		STN EN 1622	N

K<sub>3</sub> – concentration of migrating substances of the 3<sup>rd</sup> parallel migration test for migration time 72 hours and temperature (23 ± 2) °C

K<sub>0; 3</sub> – average value of concentration of migrating substances in parallel blank experiment for migration time 72 hours and temperature (23 ± 2) °C

**Notes to the tables No.1 - No.3 :**
<sup>1)</sup> symbol "<" means less than limit of method detection

<sup>2)</sup> Uncertainty means expanded combined standard relative uncertainty (extension factor k = 2)

<sup>3)</sup> A - accredited test, N - nonaccredited test

<sup>5)</sup> TFN (taste threshold)

(deg.) - degree / unit for taste according to STN EN 1622

P-01, P-03 Internal regulation LABEKO,s.r.o.

**Test report no.: 25/00817**

Page no. 3 out of 4

**Table No.4**  
**The sample No. 25-000994 Ball valve DN25 Series Gold (Art. : GRDV031).**  
**Summary results of the testing according to Decree No. 550/2007 Coll.**

Parameter	Units	$K_{72^{23}} ;1$	$K_{72^{23}} ;2$	$K_{72^{23}} ;3$	Limit values <sup>1)</sup>	Evaluation	$M_{24^{23}} ;3$ (mg.dm <sup>-2</sup> . day <sup>-1</sup> ) or (µg.dm <sup>-2</sup> . day <sup>-1</sup> )
Cadmium (Cd)	µg/l	< 1,0	< 1,0	< 1,0	5,0	meets	< 0,0156
Lead (Pb)	µg/l	< 2,0	< 2,0	< 2,0	10,0	meets	< 0,0312
Nickel (Ni)	µg/l	< 2,0	< 2,0	< 2,0	20,0	meets	< 0,0312
Copper (Cu)	mg/l	0,065	0,095	0,060	2,0	meets	0,00094
Chromium (Cr)	µg/l	< 5,0	< 5,0	< 5,0	50,0	meets	< 0,078
Antimony (Sb)	µg/l	< 3,0	< 3,0	< 3,0	10,0	meets	< 0,0468
Tin (Sn)	mg/l	< 0,005	< 0,005	< 0,005	3,0 *	meets	< 0,00008
Zinc (Zn)	mg/l	0,215	0,170	0,125	3,0 *	meets	0,0020
pH	-	6,57	6,55	6,54	6,5 - 9,5	meets	-
Taste (TFN) <sup>2)</sup>	deg.	-	-	1	max. 2	meets	-

$K_{72^{23}} ;1$  - concentration of migrating substances expressed as arithmetic mean of parallel determinations after subtraction of blank conc. for the 1<sup>st</sup> migration test at (23 ± 2)°C and time 72 hours  
 $K_{72^{23}} ;2$  - concentration of migrating substances expressed as arithmetic mean of parallel determinations after subtraction of blank conc. for the 2<sup>nd</sup> migration test at (23 ± 2)°C and time 72 hours  
 $K_{72^{23}} ;3$  - concentration of migrating substances expressed as arithmetic mean of parallel determinations after subtraction of blank conc. for the 3<sup>rd</sup> migration test at (23 ± 2)°C and time 72 hours  
 $M_{24^{23}} ;3$  - migration value of the 3<sup>rd</sup> migration test calculated from  $K_{72^{23}} ;3$  for temperature (23 ± 2) °C and for migration time 24 hrs

**Notes to the tables No.4 :**

- <sup>1)</sup> limit value according to Annex No.1 to the Decree No. 91/2023 Coll. as amended  
<sup>2)</sup> TFN (taste threshold)  
\* limit value for Zinc and Tin according to Decree No. 409/2005 Coll., paragraph 3, section 6  
symbol "<" means less than limit of method detection  
(deg.) - degree / unit for taste according to STN EN 1622

**Compliance / non-compliance with requirements :**

The evaluation of the product **Ball valve DN25 Series Gold (Art. : GRDV031)** intended for contact with drinking water was carried out according to the requirements of Decree of Ministry of Health of the Slovak Republic No.550/2007 Coll. and according to the requirements of Decree of Ministry of Health of the Slovak Republic No. 91/2023 Coll. as amended. Verification of health requirements and the evaluation of the test results according to Decree No. 550/2007 Coll., paragraph 3 was performed according to the Annex of this Decree.

For the health evaluation of the tested product were used according to annex of Decree of Ministry of Health of the Slovak Republic No. 550/2007 Coll., section 13, concentrations of migrated substances from the 3<sup>rd</sup> migration test ( $K_{72^{23}} ;3$ ). According to the Act No.103/2015 Coll., paragraph 18 ( Products intended for contact with drinking water) the amount of released substances from the products intended for the contact with drinking water must not exceed the limit values of these substances for drinking water according to Decree of Ministry of Health of the Slovak Republic No. 91/2023 Coll., Annex 1.

The measured values and results of the determination of migrating substances are given in the Tables 1 to No.3. The calculated concentrations of migrating substances from the 3<sup>rd</sup> migration test ( $K_{72^{23}} ;3$ ) listed in the Table No.4 **do not exceed** relevant limit values of these substances.

The tested product does not affect sensory properties (taste) of drinking water.

**Test report no.: 25/00817**

Page no. 4 out of 4

The results of the assessment according to Decree of Ministry of Health of the Slovak Republic No. 550/2007 Coll. indicate :

The tested product " Ball valve DN25 Series Gold (Art. : GRDV031) " manufactured by ZHEJIANG FANSHENG FLUID CONTROL CO., LTD, Putian Industrial Area, Chumen Town, Yuhuan City, Zhejiang Province 317605, China meets the requirements of Decree of Ministry of Health of the Slovak Republic No.550/2007 Coll. for the products intended to come into contact with drinking water.

Based on the achieved results of the health evaluation we can recommend the tested product for the direct contact with drinking water.

Photograph of the tested product :

The sample No. 25-000994 Ball valve DN25 Series Gold (Art. : GRDV031)




**Notice :**

Our statement only refers to the materials of the submitted sample of the product. The conclusions resulting from this evaluation may be applied also to other similar products (of this manufacturer) intended into contact with drinking water provided that used materials (direct coming into contact with drinking water) in this products are identical and their composition and properties completely correspond to the sample of the product we tested.

*Testing equipment and measuring tools used for testing were calibrated and verified within the meaning of the valid metrological directives.*

*The test results refer exclusively to the subject of the test and they do not substitute other documents (e.g. of administrative character) which are, under the specific directives, required by the bodies of governmental professional supervision. The protocol may be copied only as a whole; in parts only with the permit of the testing laboratory.*

The test report approved by : Ing. Roman Hudec  
the Head of Ecoanalytic laboratories



\*\*\* End of Report \*\*\*